

Quality Control Sub- Division

Road Division, Pipra

REPORT ON GRADATION FOR COARSE GRADED GRANULAR SUB BASE


Name of Work: Construction of Road from Saraigarh (Garia chowk) to Refugee colony under Indo-Nepal Border Road Project under supaul district for the Year-2012-13

AGREEMENT NO. : 51 SBD/2012-13
 DISTRICT : SUPAUL
 D.O.S : 25/12/2012
 D.O.C : 24/12/2014

SAMPLE NO. :
 DESCRIPTION OF MATERIAL :
 LOCATION : In the Lab of Agency
 TESTED BY : A.E Pipra
 DATE OF SAMPLING : 18/05/2017
 SAMPLED BY : A.E
 DATE OF TESTED : 18/05/2017
 LAYER : GSB 2nd layer 23+200 LHS
 WEIGHT OF SAMPLE TAKEN : 26500 gm

SIEVE SIZE	WEIGHT RETAINED	% wt RETAINED	COMM. % wt. RETAINED	% PASSING	GRADE-I LIMIT
75MM	—	—	—	100	100
26.5MM	7592	28.65	28.65	71.35	55-75
4.75MM	11925	45.0	73.65	26.35	10-30
0.075MM	6421	24.23	97.88	2.12	<10

1. E.E Road Division , Pipra (Supaul)
 1. A.E Road Division , Pipra (Supaul)

In the lab of Agency

 Assistant Engineer
 Q/c sub - Division
 Pipra, (Supaul)

**Quality Control Sub- Division
Road Division, Pipra**

REPORT ON GRADATION FOR COARSE GRADED GRANULAR SUB BASE

Name of Work: Construction of Road from Saraigarh (Garia chowk) to Refugee colony under Indo-Nepal Border Road Project under supaul district for the Year-2012-13

AGREEMENT NO. : 51 SBD/2012-13
DISTRICT : SUPAUL
D.O.S : 25/12/2012
D.O.C : 24/12/2014

SAMPLE NO. :
DESCRIPTION OF MATERIAL : GSB
LOCATION : 24+400 LHS
TESTED BY : A.E Pipra
WEIGHT OF SAMPLE TAKEN : 27000 gm

DATE OF SAMPLING : 22/05/2017
SAMPLED BY : A.E
DATE OF TESTED : 22/05/2017
LAYER : GSB 2nd layer

SIEVE SIZE	WEIGHT RETAINED	% wt RETAINED	COMM. % wt. RETAINED	% PASSING	GRADE-I LIMIT
75MM	—	—	—	100	100
26.5MM	7768	28.77	28.77	71.23	55-75
4.75MM	12447	46.1	74.87	25.13	10-30
0.075MM	6356	23.54	98.41	1.59	<10

Pan - 429

- E.E Road Division , Pipra (Supaul)
- A.E Road Division , Pipra (Supaul)

In the lab of Agency

[Signature]
22/05/17
Assistant Engineer
Q/c sub - Division
Pipra, (Supaul)